

SBS Modified Waterproofing Membrane

DESCRIPTION

BITUMAT PREMIERFLEX-3000 GL is an SBS modified bitumen waterproofing membrane re-inforced with nonwoven glassfiber mat. The combination gives the proven waterproofing qualities of bitumen along with excellent resistance to weathering and ease of application.

USES

BITUMAT PREMIERFLEX-3000 GL is a general purpose waterproofing membrane and is excellent in multi- layer or single layer roofing system. BITUMAT PREMIERFLEX-3000 is ideal as an exposed top layer. Suitable for cold or hot climates.

OUTSTANDING FEATURES

- Good cold weather resistance
- High tensile strength and tear resistance
- Good dimensional stability and recovery
- Very good puncture resistance
- Resistant to substrate movement

GENERAL DATA

Nominal Roll length	: 10 Mtrs.
Nominal Roll width	: 1M
Nominal Thickness	: 3,4 MM
Reinforcement	: Nonwoven glass fiber

PACKAGING

- 3mm - 28 rolls / pallet
- 4mm - 23 rolls / pallet

FINISHES

BITUMAT PREMIERFLEX-3000 GL is available in

- Black smooth finish with polyethylene surfaces for covered applications.
- Aluminium for exposed applications.

QUALITY CONTROL

In addition to stringent regular tests by BITUMAT laboratory, our products are tested periodically by Independent Laboratories like SOCOTEC.

STANDARDS

BITUMAT PREMIERFLEX-3000 GL complies with the requirements and tolerance levels of :

1. The American Society for Testing and Materials ASTM D 6163 Type I.
2. European Union of Technical Agreement (UEAtc)
3. MOAT 31-1984 and MOAT 30-1984.
4. CGSB (Canadian General Standards Board) 37-GP56M-July 1980.

INSTALLATION TOOLS REQUIRED:

Gas torch, Knife, Trowel, Measuring tape, Marking string and Gloves.

APPLICATION

BITUMAT PREMIERFLEX-3000 GL is installed by torch welding method, loose-laid or fully bonded to substrate. When loose-laid, only overlaps are bonded together. Peripheres and protrusions are sealed according to specifications.

COVERAGE RATE (Approx.)

(Rate may vary as per site requirement)

Flat areas : 1.15 M²/M² per layer with 10 cms. side laps and 15 cms. end laps.

Base flashing : 100x35 cms. with 15 cm. end laps, 0.40 M²/ linear M

Average wastage : 3 - 5 %

TORCHING GUIDELINES

The underside of the membrane should be torched just enough to superficially melt the bitumen. Excessive heating may damage the re-inforcement.

Overlaps should be re-heated from the top and resealed with a trowel to ensure seam integrity.

For details of installation methods and flashing requirements, consult the relevant *BITUMAT Systems Design and Installation Manual*.

SBS Modified Waterproofing Membrane

TECHNICAL DATA

MBM09 MAY04 R-00 00

	Property	Typical Value	Test Method
1.	Softening point, °C	115	ASTM D 36
2.	Penetration, @ 25 °C dmm	30	ASTM D 5
3.	Low temperature flexibility, °C	-15 to -18	ASTM D 5147
4.	Heat resistance, Compound stability @ 102 °C for 2 hours & 15 minutes	No flow - Pass	ASTM D 5147
5.	Tensile strength, N/5 cm @ 23+2 °C Longitudinal Transverse	800 (16 KN/m) 600 (12 KN/m)	ASTM D 5147
6.	Tensile strength, N/5 cm @ -18+2 °C Longitudinal Transverse	1000 (20 KN/m) 750 (12.5 KN/m)	ASTM D 5147
7.	Elongation, % @ 23+2 °C Longitudinal Transverse	40 45	ASTM D 5147
8.	Elongation, % @ -18+2 °C Longitudinal Transverse	25 25	ASTM D 5147
9.	Load strain product @ 23+2 °C Longitudinal Transverse	32,000 27,500	CGSB-37-GP-56M
10.	Load strain product @ -18+2 °C Longitudinal Transverse	25,000 18,750	CGSB-37-GP-56M
11.	Lap joint strength, N/5 cm @ 25+2 °C Longitudinal Transverse	Same as membrane	CGSB-37-GP-56M UEAtc
12.	Tear resistance, N @ 23+2 °C Longitudinal Transverse	400 400	ASTM D 5147
13.	Puncture resistance, N @ 25+2 °C Static indentation Dynamic indentation	950 L ₃ I ₃	ASTM E 154, UEAtc 5.1.9. UEAtc 5.1.10
14.	Water absorption, % Wt @ 23°C / 24 hrs.	<0.25	ASTM D 5147
15.	Water vapour transmission, g/m ² /24 hrs.	<0.30	ASTM E 96 procedure E 37.8 °C at 90% RH
16.	Dimensional stability, % Longitudinal Transverse	+ 0.5 + 0.5	ASTM D 5147
17.	Resistance to leakage at joints	Pass	UEAtc
18.	Resistance to aging & U.V.	No change greater than 20% of the original values	ASTM G53 UNI 8202

The information given in this Technical Data Sheet reflects typical median properties based on laboratory test, and practical experience; subject to the tolerance levels of UEAtc directives. However, as the product is often used under conditions beyond our control, we can't warrant but the product itself.

THIS PUBLICATION AUTOMATICALLY SUPERSEDES ALL PREVIOUS PUBLICATIONS RELATING TO THIS PRODUCT.