



BITUMAT
بيتومات

القوة في العمل

القوة في الأداء



NRCA MEMBER



ISO CERTIFIED

BITUTECT - II (O)

Oxidized Bitumen Protection Membrane

DESCRIPTION

BITUMAT BITUTECT-II(O) is a uniquely formulated, prefabricated protecting membrane with a special multi-layered design for superior pliability, tensile strength, puncture resistance and resistance to natural elements.

The multi-layered design consists of heavy duty polyester mat core, saturated, then coated on both sides with oxidized bitumen. The heavy duty polyester core gives the membrane high tensile strength, elongation, puncture resistance and superior lap joint strength.

Properly installed BITUMAT BITUTECT-II(O) forms a durable, lightweight protection membrane for shielding the waterproofing from abrasive backfill, site damage, and re-inforcement fixing.

USES

BITUMAT BITUTECT-II(O) membranes are ideal as a protection membrane to protect waterproofing systems that may be on roofs, reservoirs, basements, tunnels and car parks. Due to its superior mechanical properties, it resists sharply angled aggregates from damaging the waterproofing system. The polyethylene sheet on both the sides also adds to the protection property of BITUMAT BITUTECT-II(O).

OUTSTANDING FEATURES

- Total protection to waterproofing systems
- Very high resistance to impact and puncture
- Impermeable to water
- Outstanding bondability and seam integrity
- Flexibility at low temperatures
- Stability at high temperatures
- Simple, single-layer installation reduces labour and errors

GENERAL DATA

BITUMAT BITUTECT-II(O) is a plasticized bitumen membrane with a heavy duty non-woven polyester re-inforcement, black finish with a very thin polyethylene foil on both sides.

Nominal Weight	: 4.8 Kg/M ²
Nominal Thickness	: 4 MM
Nominal Roll Size	: 1x10 Mts.

INSTALLATION

BITUMAT BITUTECT-II(O) can be installed by torch welding or by adhesive or by using hot bitumen. If torching method is used, the under side of the membrane should be torched just enough to superficially soften the bitumen. Excessive heating may damage the re-inforcement.

The roll can be installed either by giving 5-10 cm overlaps or can be laid by butting the sides together.

On vertical surfaces the material should be temporarily held in place or fixed with an adhesive such as BITUMAT BITUFLASH with the waterproofing membrane.



BITUMAT
بيتومات

BITUTECT - II (O)

Oxidized Bitumen Protection Membrane

TECHNICAL DATA

PTM 02	30-E	R-00	00
--------	------	------	----

	Property	Typical Value	Test Method
1.	Softening point, °C	115 ± 5	ASTM D 36
2.	Penetration @ 25°C, dmm	20 ± 5	ASTM D 5
3.	Tensile strength, N/5 cm Longitudinal Transverse	550 450	UEAtc; ASTM D 5147 UEAtc; ASTM D 5147
4.	Elongation, % Longitudinal Transverse	45 45	UEAtc; ASTM D 5147 UEAtc; ASTM D 5147
5.	Tear resistance, N Longitudinal Transverse	Min. 150 Min. 160	UEAtc UEAtc
6.	Puncture resistance Static indentation Dynamic indentation	30 kg I ₃	UEAtc UEAtc
7.	Resistance to chlorides, sulphides and sulphates	Good	In-House Test
8.	Resistance to alkaline or acidic environment	Good	In-House Test
9.	Puncture resistance, N/32 mm	800 N/32mm	ASTM E 154
10.	Water absorption	0.70	ASTM D 5147 Sect. 9
11.	Inorganic filler	>27%	In-House Test
12.	Density	1.25	ASTM D 2389-97

The information given in this Technical Data Sheet reflects typical median properties based on laboratory test, and practical experience; subject to the tolerance levels of UEAtc directives. However, as the product is often used under conditions beyond our control, we can't warrant but the product itself.

THIS PUBLICATION AUTOMATICALLY SUPERSEDES ALL PREVIOUS PUBLICATIONS RELATING TO THIS PRODUCT.

BITUMAT COMPANY LIMITED

Corporate Office : P.O. Box 7487, Dammam 31462, Kingdom of Saudi Arabia Tel. No. (966-3) 8121210 / 8121213 Fax No. (966-3) 8121190
 Central Region : P.O. Box 56686, Riyadh 11515, Kingdom of Saudi Arabia Tel. No. (966-1) 4770443 / 4792553 Fax No. (966-1) 4762318
 Western Region : P.O. Box 12005, Jeddah 21483, Kingdom of Saudi Arabia Tel. No. (966-2) 6644489 Fax No. (966-2) 6640559
 Email : marketing@bitumat.com / Website: www.bitumat.com



NRCA MEMBER



ISO CERTIFIED